

laguna

product data

interiors, commercial, retail, institutional applications

environmentally preferable

test results

slip (astm c-1028) 0.85 dry / 0.88 wet
slip (AS/NZS 4586) BPN: 36, Class: X, R10 (HB-197 equiv.)
compressive: 8702psi / 60mpa
tensile: 1401psi / 9.6mpa

technical summary

weight (lb/sq.ft): 3/8" = 5 10mm = 25
(kg/m2): 5/8" = 7.5 15mm = 38
3/4" = 10 20mm = 50
1" = 12.5 25mm = 63
size/rectangularity: ± 0.75mm
thickness: ± 2mm
max curvature: ± 0.5 percent of max tile length

slip and abrasion resistant for hightraffic use

dimensionally accurate standard and custom formats

installation

substrate: level
cured to max 5.5 percent moisture
adhesive: mapei granirapid
min grout joint: ± 0.5 percent of max tile length
expansion joints: 20' (6m) max interval
process: thinset installation
hand set only
backbutter
clean: scrub with floor machine
use htc twister™ pads (white/green)
neutral detergent (non acidic)
refer to our floor cleaning guide
seal: refer to our product sealer guide



contact our technical team for assistance related to your specific installation. we also offer adhesive, sealers, buffing pads, and contractor services in an effort to streamline your procurement process and better support your project.