

product data

exterior, commercial, hospitality, institutional applications

environmentally preferable

test results

slip (astm c-1028)	flekk/terrazzo: 0.93 dry / 0.83 wet
	textured: 0.88 dry / 0.89 wet
slip (AS/NZS 4586)	flekk/terrazzo: BPN: 59, Class V
	textured: BPN: 62, Class V
compressive:	>10500psi / 72mpa
tensile:	>1500psi / 10.3mpa

technical summary

weight (lb/sq.ft):	3/4" = 10	20mm = 50
(kg/m2)	1 1/4" = 15	30mm = 75
	2" = 25	50mm = 125
size/rectangularity:	± 0.75mm	
thickness:	± 2mm	
max curvature:	± 0.5 percent of max tile length	
min grout joint:	3/16"	

slip and abrasion resistant for high use

dimensionally accurate standard and custom formats

installation

method:	
3/4"	thin-set with mapei granirapid
1 1/4"	mortar (preferred)
2"	sand / pedestal

- * consult with us to determine your specific project needs.
- * for 2" thick planks mortar set only

min grout joint:	3/16"
expansion joints:	15' (4.5m) max interval where required
process:	contact us for specific installation method / process
clean:	scrub with neutral cleaner
seal:	refer to our product sealer guide



contact our technical team for assistance related to your specific installation. we also offer adhesive, sealers, buffing pads, and contractor services in an effort to streamline your procurement process and better support your project.