

# venice

## product data

interiors, commercial, retail, institutional applications

environmentally preferable

## test results

slip (astm c-1028) 0.90 dry / 0.65 wet  
compressive: 8702psi / 60mpa  
tensile: 1401psi / 9.6mpa

## technical summary

weight (lb/sq.ft):	3/8" = 5	10mm = 25
(kg/m2)	5/8" = 7.5	15mm = 38
	3/4" = 10	20mm = 50
	1" = 12.5	25mm = 63
	1 1/4" = 12.5	30mm = 75
size/rectangularity:	± 0.75mm	
thickness:	± 2mm	
max curvature:	± 0.5 percent of max tile length	

slip and abrasion resistant for high traffic use

tile and slab sizes available

## installation

substrate:	level cured to max 5.5 percent moisture
adhesive:	mapei granirapid
min grout joint:	± 0.5 percent of max tile length
expansion joints:	20' (6m) max interval
process:	thinset installation hand set only backbutter
clean:	scrub with floor machine use htc twister™ pads (white/green) neutral detergent (non acidic) refer to our product cleaning guide
seal:	refer to our product sealer guide



contact our technical team for assistance related to your specific installation. we also offer adhesive, sealers, buffing pads, and contractor referrals in an effort to streamline your procurement process and better support your project.

collaborate

concrete-collaborative.com  
sales@concrete-collaborative.com

concrete  
collaborative